



Trinity 1945

auto paint and supplies
Satisfying Customers Since 1998

www.PaintForCars.com

Open Monday - Friday - 9am to 5pm EST
Customer Support: autopaint@paintforcars.com
To speak to a Sales Representative, call 848-448-8186

NON-SANDING GRAY PRIMER:

Non-sanding gray primer has great filling and sanding properties, excellent holdout, fast dry, and good adhesion on properly prepared substrates.

Suitable Substrates:

Existing finishes, properly sanded, in good condition.



Surface Preparation:

If necessary, pre-wash the surface with warm water and soap, rinse sufficiently with clean water and dry.

Spray gun set-up/application pressure

Fluid tip-set up
Gravity feed 1.6- 2.0 mm

Application pressure
29 psi at the spray gun air inlet HVLP max 10 psi at the air cap.

Wet on wet
Gravity feed 1.3 - 1.5 mm

29 psi at the spray gun air inlet HVLP max 10 psi at the air cap

Film Thickness:

Non-sanding sealer (mixing ratio) 4:1 1 coat 1.0 - 1.2 mils (25- 30 um)

Drying Time:

3 hours at 70 degree F 30 minutes @ 140 degree F

Drying times relate to recommended application (3 - 4 coats)
and object temperature

Theoretical

Coverage:

96 Square feet /liter

Use suitable respiratory protection - recommends the use of a fresh air supply respirator.